

| Parameter                 | Test Method | Unit    | Nominal Value                                  |       |           |       |
|---------------------------|-------------|---------|------------------------------------------------|-------|-----------|-------|
|                           |             |         | Round Rope                                     |       | Flat Rope |       |
|                           |             |         | 5mm                                            | 8mm   | 10mm      | 12mm  |
| Composition               | Outer Cover |         | 100% Solution Dyed Acrylic                     |       |           |       |
|                           | Inner Core  |         | 100% PES                                       |       |           |       |
| Weight                    |             | G/M     | 12.50                                          | 34.75 | 17.50     | 20.00 |
| Finish                    |             |         | Water-repellent with stain-resistant treatment |       |           |       |
| Color Fastness UV Outdoor | ISO 105-B02 | Class/8 | 8                                              | 8     | 8         | 8     |
| Tensile Strength          | ISO 6892    | Kgs     | 500                                            | 1000  | 250       | 250   |
| Elongation at break       | ISO 2307    | %       | 12                                             | 12    | 12        | 12    |
| Pilling Resistance        | ISO 12945   | Class/5 | 4-5                                            | 4-5   | 4-5       | 4-5   |